

PLASMA RESISTANT MEMBER

Patent number: JP10236871
Publication date: 1998-09-08
Inventor: MURAKAWA SHUNICHI; NAKAMURA KATSUMI
Applicant: KYOCERA CORP
Classification:
- International: C04B35/44; C23C16/50; H01L21/22; H01L21/68; H05B3/14
- european:
Application number: JP19970042604 19970226
Priority number(s):

Abstract of JP10236871

PROBLEM TO BE SOLVED: To obtain a member having superior plasma resistance in an atmosphere of halogen-contg. corrosive gas by forming the surface of a member exposed to plasma in the atmosphere with a Y-Al-garnet sintered compact having specified porosity and specifying the surface roughness.

SOLUTION: The surface of a member exposed to plasma in an atmosphere of halogen-contg. corrosive gas such as F- or Cl-contg. gas is formed with a Y-Al-garnet sintered compact having $\leq 3\%$ porosity and the center line average surface roughness Ra is regulated to $\leq 1\mu\text{m}$. Plasma resistance to the halogen- contg. corrosive gas can further be improved by reducing the total amt. of oxides of group Ila elements of the Periodic Table and SiO₂ contained in the sintered compact to $\leq 1,500\text{ppm}$. The resultant plasma resistant member is useful to produce constituent parts of a semiconductor producing device having a long service life.

Data supplied from the esp@cenet database - Patent Abstracts of Japan